



Regupol®

TECHNICAL DATA SHEET

EVERROLL® KOMBI

PRODUCT DESCRIPTION

everroll® Kombi is a prefabricated (alternatively laminated on site), point elastic, sprint track or plyometric surface for sprint and speed training in fitness studios. Due to its double layer construction everroll® Kombi offers an adequate force reduction protecting subfloors. The resilient base mat provides a significant energy reduction which protects athlete's joints under high strains. The EPDM top layer is slip-resistant and extremely durable.

APPLICATIONS

Sports, fitness and contract flooring.

MATERIAL COMPOSITION

Elastic flooring mat, made of selected rubber granulates bound with polyurethane, laminated with a wearing surfaces mat made from selected EPDM granulates.

Different make-ups available to suit specific force reduction requirements:

4+4 - 4mm elastic base layer/ 4mm EPDM top layer

6+4 - 6mm elastic base layer/ 4mm EPDM top layer

8+4 - 8mm elastic base layer/ 4mm EPDM top layer

COLOUR PATTERN

Base mat: Black

Wearing surface: Red, Blue or Green



PHYSICAL INFORMATION

	4 + 4	6 + 4	8 + 4
Thickness (mm)	8	10	12
Weight per m ²	8.84kg	10.32kg	11.80kg
Force Reduction (DIN 3802)	20%	25%	32.4%
Temperature Resistance	- 40° C to 115° C		
Fire Resistance (EN 13501-1)	Class E		

Notice: The above mentioned test data are based on periodical laboratory testing of test specimen taken from the actual manufacturing process and show the average values measured. The publishing of these technical data does not relieve the user of the necessity to test the relevant product for physical fitness based on a specific application. As the final use and application of our products are out of our control, this is the sole responsibility of the buyer / end user. All of our products do carry a warranty against manufacturer's defects according to our standard terms and conditions of sale. Due to deviations in raw materials, external influences like temperature and humidity variations, and the fact that this data relates to a resilient material, the above mentioned values are subject to vary up to +/- 25%.

CMS DANSKIN ACOUSTICS

Scotland Office: Tel: **01698 356000** Fax: **01698 372222**
1 Netherton Road Wishaw ML2 0EQ

Central/Southern Office: Tel: **01925 577711** Fax: **01925 577733**
Unit 2 Lyncastle Road, Appleton, Warrington, WA4 4SN

Email: info@cmsdanskin.co.uk Website: www.cmsdanskin.co.uk

IMPORTANT: Goods supplied by the company are made to approved standards from the highest quality raw materials but no warranty or guarantee is given as to their suitability for any particular purpose or application, and no liability is accepted for any loss or damage arising directly or indirectly from the use of the Company's products irrespective of any information given to us as to intended use of such products. It is therefore recommended that prospective users should test a sample of this product under their own conditions to satisfy themselves that the product is suitable for the purpose intended.

CMSDANSKIN
ACOUSTICS

